

422X Series High Solids Topcoat

Technical Data Sheet

Product Group

Epoxy topcoat

Characteristics



Product
Information

A two-component, chemically cured epoxy topcoat designed to provide chemical resistance coupled with sufficient flexibility to minimize chipping and flaking. This epoxy topcoat can be used with various primers. Normally military specification primers MIL PRF 85582, MIL-PRF-23377 or MIL DTL 53022 are recommended.

Components



Curing Solution
Thinner /
Activator

Gloss Curing Solution:	0200T129
Flat Curing Solution:	0200T126
Flat Curing Solution for MIL-PRF-22750 TY II	0200T126C

Specifications



Qualified
Product List

Air France	SMI 70 132-1
Military US	MIL-PRF-22750 TY II for only the following colors:
	595B-17178
	595B-17925
	595B-16492
	595B-36231
	595B-37038

All other colors meet the Performance of MIL-PRF-22750 TY I.

For most recent up-date or missing specifications please check the qualified product list (QPL) on www.akzonobel.com/aerospace.

Surface Conditions



Cleaning

- Surface pretreatment is an essential part of the painting process.
- Follow the specification requirements for cleaning and pretreatment application.

422X Series High Solids Topcoat

Instruction for Use



Mixing Ratio
(volume)

3 parts
1 part

Gloss

Base 422X Series
Curing Solution 0200T129

Flat

Base 422X Series
Curing Solution 0200T126

3 parts
1 part

- Stir or Shake until all pigment is uniformly dispersed before adding curing solution.
- Stir the catalyzed mixture thoroughly



Induction Time

30 minutes.



Initial Spraying
Viscosity
(25°C/77°F)

50 seconds maximum (#4 Ford) admixed.
75 seconds maximum (#4 Ford) at pot life.

The uses of Ford Cups for viscosity are requirements of the referenced specifications, and provided only as a reference for field application. They are not provided as quality control values. Actual values will vary when tested outside of standard conditions (25°C/77°F).



Note

Viscosity measurements are provided as guidelines only and are not to be used as quality control parameters. Certified information is provided by certification documentation available on request.



Pot life
(25°C/77°F)

4 hours.



Dry Film
Thickness
(DFT)

1.8 – 2.2 mils .
46 – 56 microns.

422X Series High Solids Topcoat

Application Recommendations



Conditions

Temperature: 15 – 35°C
59 – 95°F
Relative Humidity: 35 – 75%



Note

The quality of the application of all coatings will be influenced by the spray equipment chosen and the temperature, humidity, and air flow of the paint application area. When applying the product for the first time, it is recommended that test panels be prepared in order to identify the best equipment settings to be used in optimizing the performance and appearance of the coating.



Equipment

Standard suction, pressure, HVLP or airless spray.



Number of Coats

Spray a uniform wet coat. Flash 10-15 minutes, then apply a second wet coat to recommended dry film thickness.



Cleaning of
Equipment

Use TR-19 for cleanup. This balanced thinner will minimize the possibility of residue remaining on the equipment.

422X Series High Solids Topcoat

Physical Properties



Drying Times
(25 +/- 2°C / 77
+/- 2°F, 55 +/- 5%
RH)

Dry to touch 3 hours
Dry to tape 8 hours
Full cure 14 days

Accelerated Cure

Dry to tape / handle 2 hour flash off at ambient, then 20 – 30 minutes at 140°F (60°C)

Full cure 24 hour flash off at ambient, then 24 hours @ 150°F (65.5°C)



Note

CAUTION: The accelerated cure for dry to tape / handle may cause a slight variation to color and/or gloss in some topcoats. Light colors, e.g., white and off white, in the semi gloss range could be affected.

NOTE: The cure required will vary due to the efficiency of the oven being used (evacuating the solvent heavy air) and the amount of air movement in the oven. The customer should run tests to verify the required cure schedule.



Theoretical Coverage

20.3 – 22.1 m² per liter ready to apply at 25 µm dry film thickness
825 – 900 ft² per US gallon ready to apply at 1 mil dry film thickness



Volatile Organic Compounds

Max 340 g/l
Max. 2.8 lb/gal



Dry Film Weight

Gloss

39.3 ± 3.0 g/m²/25 µm micron
0.0080 ± 0.0008 lbs/ft²/mil

Flat

46.3 ± 3.0 g/m²/25 µm micron
0.0094 ± 0.0008 lbs/ft²/mil

422X Series High Solids Topcoat



Gloss (60°)

Gloss

90+

422XT1XXXXX* / 0200T129

Camouflage

5 maximum (9 maximum 85°)

422XT3XXXXX* / 0200T126

*Last 5 digits refer to 595B Federal Standard Color



Color

As required:

595-16492

595-17178

595-36231

595-37038

595-17925



Flash-point

422X Series

-4°C / 25°F

0200T126

27°C / 80°F

0200T129

36°C / 97°F



Storage

Store the product dry and at a temperature between 5 and 38°C / 40 and 100°F per AkzoNobel Aerospace Coatings specification. Store in the original unopened containers. Storage temperature may vary per OEM specification requirements. Refer to container label for specific storage life information.

Shelf life

5 - 38°C

(40 - 100°F)

24 months per AkzoNobel Aerospace Coatings commercial specification. Shelf life may vary due to OEM specification requirements. Refer to container label for specific shelf life information.

Safety Precautions

Comply with all local safety, disposal and transportation regulations. Check the Material Safety Data Sheet (MSDS) and label of the individual products carefully before using the products. The MSDS's are available on request.

422X Series

High Solids Topcoat

Issue date: January 2015 (supersedes August 2009) - FOR PROFESSIONAL USE ONLY

IMPORTANT NOTE The information in this data sheet is not intended to be exhaustive and is based on the present state of our knowledge and on current laws: any person using the product for any purpose other than that specifically recommended in the technical data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at his own risk. It is always the responsibility of the user to take all necessary steps to fulfill the demands set out in the local rules and legislation. Always read the Material Data Sheet and the Technical Data Sheet for this product if available. All advice we give or any statement made about the product by us (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing otherwise, we do not accept any liability whatsoever for the performance of the product or for any loss or damage arising out of the use of the product. All products supplied and technical advice given is subject to our standard terms and conditions of sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is subject to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to verify that this data sheet is current prior to using the product.

Brand names mentioned in this data sheet are trademarks of or are licensed to AkzoNobel.
